

DuPont™ Sontara®

| TECHNICAL DATA – STYLE K902S | | | | |
|---------------------------------------|-----------|-------------------|-------------|------------|
| Property | Value | Unit | Test method | |
| Composition | Polyester | 48 | % | |
| | Woodpulp | 52 | % | |
| Basis weight | 53 | g/m ² | WSP 130.1 | |
| Thickness | 0.49 | mm | WSP 120.6 | |
| Absorbency | 623 | % | WSP 10.1 | |
| Extrinsic absorption capacity | 348 | ml/m ² | WSP 10.2 | |
| Grab tensile breaking strength (dry) | MD | 110 | N | ASTM D5034 |
| | XD | 56 | N | |
| Strip tensile breaking strength (dry) | MD | 107 | N | WSP 110.4 |
| | XD | 38 | N | |

Preliminary data based on limited sampling. For guidance only



www.Sontara.com
Tel. 1-888-4-SONTARA

The miracles of science™

All properties are typical values based on roll averages. This is not a specification. Please conduct your own tests to ensure consistency for your application. This information is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. No right or licence to any intellectual property of DuPont is intended by the publication of these properties.

Nominal values corresponding to our current knowledge, for guidance only. MD=lengthwise, XD=crosswise – last update 25/04/2008

© 2005 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and Sontara® are registered trademarks of DuPont or its affiliates.